

5W40 B7 Status

B7 Status SAE 5W40 is a Synthetic lubricant for long-life petrol and diesel engines (with and without catalytic converter, including high-performance turbo and multi-valve GTI - TDI). With high-performance turbo and multi-valve GTI - TDI (Long Life) in service and high performance, due to its high quality, it also stands out for its low consumption over the kilometers. The recommended maintenance intervals are 20,000 Km. It has excellent lubrication properties, reducing friction and increasing wear resistance at high temperatures.

B7 Status SAE 5W40 ist ein synthetisches Schmiermittel für langlebige Benzin- und Dieselmotoren (mit und ohne Katalysator, einschließlich Hochleistungs-Turbo- und Mehrventil-GTI-TDI). Mit Hochleistungs-Turbo- und Mehrventil-GTI-TDI-Motoren (Long Life) im Einsatz und hoher Leistung zeichnet es sich aufgrund seiner hohen Qualität auch durch seinen geringen Verbrauch über die Kilometer aus. Die empfohlenen Wartungsintervalle betragen 20.000 km. Es verfügt über ausgezeichnete Schmiereigenschaften, reduziert die Reibung und erhöht die Verschleißfestigkeit bei hohen Temperaturen.

EIGENSCHAFTEN/ PROPERTIES:

- Geringer Verbrauch
- Hervorragende Schmiereigenschaften
- Reduziert Reibung und verhindert Verschleiß
- Low consumption
- Excellent lubricating properties
- Reduces friction and prevents wear

SPEZIFIKATIONEN/ SPECIFICATIONS:

API SN/CF ACEA A3/B3/B4

GM-LL B-025 | MB 229.5 | MB 226.5 | VW 502.00 /505.00 | BMW LL-01
Renault RN 0700/0710 | Peugeot & Citroën B712296 | Porsche A40 |
FIAT 9.55535-M2

SAFETY & HEALTH

Security data sheet are available upon request and should be consulted for more appropriate information.
The company shall not be liable for any damages caused by misuse, or if precautions are not taken.



5W40 B7 Status

TECHNISCHE DATEN / TECHNICAL CHARACTERISTICS:

5W40 B7 Status API SN/CF ACEA A3/B3/B4

Eigenschaften/Properties	Einheit/Unit	Test	Wert/Value
Density @15.6°C	g/ml	ASTM D1298	0,855
Kinematic Viscosity @ 40°C	mm ² /S	ASTM D445	82/88
Kinematic Viscosity @ 100°C	mm ² /S	ASTM D445	17/15,5
Viscosity index (VI)		ASTM D2270	165
Flash Point, Cleveland open cup	°C	ASTM D92	233
Pour Point	°C	ASTM D97	<-40
Total Base Number	mgKOH/g	ASTM D2896	>9,0
Sulphated Ash	Mass%	ASTM D874	<0,8/1

The information above is based on current production data and can vary within given tolerances. Temperature range is given as a guideline only. Information and data can be changed without previous notification. This information replaces prior editions.

